

GARON PLUG™

Quick-Setting Hydraulic Cement



DESCRIPTION

Garon Plug™ is fast setting hydraulic cement with exceptional structural strength, which may be used to repair pressure leaks in concrete masonry. **Garon Plug™** is non-shrink and does not contain metallics of any type and hence will not rust or deteriorate.

USES

Garon Plug™ is used for patching and filling cracks, blisters or spalls found in concrete masonry construction. Ideal for quick and easy repairs of precast-prestressed concrete. Anchors ornamental iron railings, bolts, dowels. Seals wall-floor joints from water seepage. Seals water leaks in dams, tunnels, sewers and other masonry construction.

PRODUCT ADVANTAGES

- Ready to use, just add water.
- Dries quickly, puts repaired area back in use sooner.
- Ideal for emergency repairs.
- Non-shrink characteristics insures a durable patch that will not pull away from edge.

YIELD/COVERAGE

- 5 gallons will fill approximately 73 linear feet measuring 3/4" x 3/4".

SURFACE PREPARATION

All dirt, oil, dust, foreign contaminants, peeling coating and laitance must be removed from surface prior to coating to assure a trouble free bond. Previously coated floors exhibiting a strong bond to surface can be coated over by sanding down the existing coating.

Refer to **Garon's Master Surface Preparation & Moisture Guideline** for complete details.

Typical Technical Data For Garon Plug™ (Product and curing conditions at 73°F and 50% R.H.)	
Storage Conditions	Store dry at 40°F - 95°F. Condition material to 65°F - 75°F before using.
Set Time (ASTM C 191)	3 Minutes
Tensile Strength (ASTM C 307)	24 Hour: 210 psi 7 Day: 305 psi 28 Day: 364 psi
Compressive Strength (ASTM C 109)	1 Hour: 1,025 psi 24 Hour: 1,625 psi 3 Day: 3,750 psi 7 Day: 4,180 psi 28 Day: 5,050 psi

MIXING

Garon Plug™ is fast setting. **Mix Only An Amount That Can Be Placed In 3 To 5 Minutes. Do Not Retender** after **Garon Plug™** has started to set. Avoid overworking. Mix only enough to be sure that the cement is thoroughly dispersed.

APPLICATION & PLACEMENT

Mix **Garon Plug™** with enough water to make a batter consistency scratch coat, then place patch using a putty consistency mixture of **GARON PLUG™**. Mix one part water, three parts **Garon Plug™** by volume. To plug streams of water, prepare surface by cutting away to sound masonry. Mix **Garon Plug™** to a putty consistency and roll between the palms to obtain the desired plug size. As material starts to set, press firmly into opening and hold under pressure with hand or trowel for a few minutes until material hardens. Shave patch to make flush with surrounding surface.

HOT WEATHER: **Garon Plug™** will set rapidly when the temperature is over 70°F. Ice water may be used to compensate for the accelerating effect of the weather. The cement should always be stored in a cool area preferably not over 70°F. Take every

effort to control the temperature factor to achieve optimum structural strength.

COLD WEATHER: **Garon Plug™** should be stored at a normal room temperature. The use of warm water and preheating the area to be patched will help the material to harden faster. As a general rule, **Garon Plug™** should not be used under 40°F, unless these precautions are observed.

LIMITATIONS

The user is responsible for proper application. Minimum ambient and surface temperatures at 45°F and rising at time of application. Use only potable water for mixing.

CLEAN UP

Clean tools with soap and water.



FIRST AID

Skin contact- wash thoroughly with soap & water. If any product gets into the eye, rinse immediately and repeatedly with water for at least 15 minutes. For respiratory problems, remove person to fresh air. Wash clothing before re-use.

Keep container tightly closed. Not for internal consumption--consult MSDS for additional information. This product is for professional use only.

KEEP OUT OF REACH OF CHILDREN

Garon and **Garon Plug™** are trademarks of
Garon Products Inc.
Made in USA.

GARON PRODUCTS INC.
P.O. Box 1924
Wall, NJ 07719-1924
800-631-5380
FAX 732-223-2002
www.garonproducts.com

Garon products are sold with the understanding that the buyer will test them in actual use and determine for himself their adaptability to his intended use. However, since such use is beyond our control, we do not guarantee the results to be obtained in the customer's processes. The information contained in this brief is advisory only, and the use of the materials and methods is solely at the risk of the user. These recommendations and suggestions for the use of our materials are in accordance with Garon standards. There are no other warranties by Garon of any nature whatsoever, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product, and under no circumstances, either expressed or implied, will GARON PRODUCTS, INC. be liable for damages in excess of the purchase price of this product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by the officers of manufacturer and direct purchaser or Garon distributor of manufacturer's material.
