

# NUTRACID™

## Acid Resistant Coating



### PRODUCT DESCRIPTION:

Nutracid™ is a two component colored high solids novolac epoxy coating designed for application where splash and spills of acids, chemicals, and solvents occur.

### RECOMMENDED FOR:

Recommended for a high build topcoat for traffic areas, chemical troughs and curbs as well as tanks and chemical spill areas for cement masonry or brick.

### SOLIDS BY WEIGHT:

96% (+/- 1%)

### SOLIDS BY VOLUME:

94% (+/- 1%)

### VOLATILE ORGANIC CONTENT:

0.40# per gallon (mixed)

### STANDARD COLORS:

Light gray, medium gray, and tile red

### RECOMMENDED FILM THICKNESS:

16-18 mils

### COVERAGE PER GALLON:

90-100 square feet per gallon @ 16-18 mils

### PACKAGING INFORMATION:

1 gallon kit (volume approximate, offered in Clear only)

1.5 gallon kit (volume approximate)

3 gallon kit (volume approximate)

### MIX RATIO:

10.15 pounds (1 gallon) part A to 4.2 pounds (.50 gallons) part B (volumes approx.)

### SHELF LIFE:

1 year in unopened containers

### FINISH CHARACTERISTICS:

Gloss (>40 at 60 degrees @ Erichsen glossmeter)

### FLEXURAL STRENGTH:

9,610 psi @ ASTM D790- 1/2"X1/2" bars span 4"

### COMPRESSIVE STRENGTH:

9,900 psi @ ASTM D695

### TENSILE STRENGTH:

6,680 psi @ ASTM D638

### ADHESION:

425 psi @ elcometer (concrete failure, no delamination)

### ULTIMATE ELONGATION:

4.7%

### HARDNESS:

Shore D = 88

### GARDNER VARIABLE IMPACTOR:

50 inch pounds direct – passed

### ABRASION RESISTANCE:

Taber abraser CS-17 calibrase wheel with 1000 gram total load and 500 cycles= 20 mg loss

### VISCOSITY:

Mixed = 2200-2700 cps (typical)

### DOT CLASSIFICATIONS:

Part A "not regulated"

Part B "CORROSIVE LIQUID N.O.S., 8, UN1760, PGIII"

### HEAT DEFLECTION TEMP:

115.5 degrees F, ASTM D648

### CURE SCHEDULE: (70°F)

pot life – (1.5 gallon volume)...25-35 minutes

tack free (dry to touch).....5-7 hours

recoat or topcoat.....5-10 hours

light foot traffic.....10-18 hours

full cure (heavy traffic).....2-7 days

### APPLICATION TEMPERATURE:

60-95 degrees F with relative humidity below 90%

### CHEMICAL RESISTANCE:

REAGENT	RATING
Xylene	D
1, 1, 1 Trichloroethane	C
Mek	C
Methanol	C
Ethyl alcohol	C
Skydrol	C
10% sodium hydroxide	E
50% sodium hydroxide	E
10% sulfuric acid	E
70% sulfuric acid	C
10% HC1 (aq)	D
5% acetic acid	D

Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.

### PRIMER:

Recommended Tigerskin™

### TOPCOAT:

None recommended

### LIMITATIONS:

- Color stability or gloss may be affected by environmental conditions such as high humidity, low temperature or chemical exposure.
- Colors may vary from batch to batch. Therefore, use only product from the same batch for an entire job.
- Apply a suitable primer before using this product

# GARON

- This product is not UV color stable and exposure to lighting such as sodium vapor lights may cause discolorations.
- Mixtures of chemicals and applications with exposures to chemicals at elevated temperatures should be thoroughly evaluated before applying coating. A test patch is recommended.
- Product can develop surface irregularities in leveling in combination to some chemical contamination or substrate compositions.
- Substrate temperature must be 5°F above dew point.
- For best results, apply with a 1/4" nap roller.
- All new concrete must be cured for at least 30 days prior to application.
- Physical properties are typical values and not specifications.

### MIXING AND APPLICATION INSTRUCTIONS

1) **PRODUCT STORAGE:** Store product in an area as to bring the material to normal room temperature before using. Continuous storage should be between 60 and 90 degrees F. Low temperatures or great temperature fluctuations may cause product crystallization.

2) **SURFACE PREPARATION:** The most suitable surface preparation would be a fine brush blast (shot blast) to remove all laitance and provide a suitable profile. All dirt, foreign contaminants, oil and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding.

3) **PRODUCT MIXING:** This product has a mix ratio of 10.15# part A to 4.2# part B for standard colors. Standard packages are in pre-measured kits and should be mixed as supplied in the kit. We highly recommend that the kits not be broken down unless suitable weighing equipment is available. After the two parts are combined, mix well with slow speed mixing equipment such as a

jiffy mixer until the material is thoroughly mixed and streak free. After mixing, transfer the mixed material to another pail (the transfer pail) and again remix. The material in the transfer pail is now ready to be applied on the primed substrate. Improper mixing may result in product failure.

4) **PRIMING:** A suitable primer should be used before applying this product. See the front side of this technical data for primer information. If a primer is not used, more porous substrates may cause outgassing and possible surface defects.

5) **PRODUCT APPLICATION:** The mixed material can be applied by brush or roller. However, the material can also be applied by a suitable serrated squeegee and then back rolled as long as the appropriate thickness recommendations are maintained. Maintain

temperatures and relative humidity within the recommended ranges during the application and curing process. If concrete conditions or over aggressive mixing causes air entrapment, then an air release roller tool should be used prior to the coating tacking off to remove the air entrapped in the coating.

6) **RECOAT OR TOPCOATING:** If you opt to recoat or topcoat this product, you must first be sure that the coating has tacked off before recoating. However, all previous coats should be deglossed to insure a trouble free bond prior to application of recoats or topcoats. Always remember that colder temperatures will require more cure time for the product before recoating or top coating can commence. Before recoating or top coating, check the coating to insure no epoxy blushes were developed (a whitish, greasy film, or deglossing.) If a blush is present, it must be

removed prior to top coating or recoating. Multiple coats of this product are acceptable and can be used to achieve greater chemical resistance and build.

7) **CLEANUP:** Use Xylol

8) **FLOOR CLEANING:** Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

9) **RESTRICTIONS:** Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle.

#### **NOTICE TO BUYER:**

#### **DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY**

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.**