

TRAFFIC-FAST™

Shallow Void Repair



DESCRIPTION

TRAFFIC-FAST™ is a new and unique development in the field of fast setting high strength cements. This select formulation of

cementitious binders and resins produces an exceptionally durable, high strength, non-shrinking repair compound. It is characterized by a fast set time (3 - 4 hours) which permits the uses of repaired surfaces thus avoiding "out of service areas" for prolonged periods of time.

USES

TRAFFIC-FAST™ is used to resurface and repair any concrete surface. Uses include spalled loading docks, plant floors, aprons, sidewalks, parking lots, aisles, hairline cracks, and potholes.

PRODUCT ADVANTAGES

- Bonds instantly to any surface.
- Steel hard set.
- No special skills needed.
- Easy pour application.

YIELD/COVERAGE

20 square feet at ¼" per 5 gallon unit.

PACKAGING

5-gallon pail

SURFACE PREPARATION

All dirt, oil, dust, foreign contaminants, peeling coating and laitance must be removed from surface prior to coating to assure a trouble free bond. Previously coated floors exhibiting a strong bond to surface can be coated over by sanding down the existing coating.

Refer to ICRI TECHNICAL GUIDELINE NO. 03732 Selecting and Specifying Concrete Surface Preparation for Coatings, Sealers, and Polymer Overlays for additional details.

MIXING

The resin and setting powder components are pre-measured so that when mixed will

TYPICAL TECHNICAL DATA FOR TRAFFIC-FAST™ (Product and curing conditions at 73°F and 50% R.H.)	
Storage Conditions	Store dry at 40°-95°F. Condition material to 65°-75°F before using.
Compressive Strength (1 hour)	2,000 psi
Compressive Strength (28 day)	8000 psi
Density	104.5 lbs per cubic foot
Freeze-Thaw Resistance	Good
Auto Ignition Temperature Horizontal furnace*	No ignition
760°C. Tempered Steel Ball Test*	No ignition
Dust Cloud Test G.G. Furnace*	No ignition
Bunsen Burner Shaker Test*	No ignition
Flash Point 0°F (Pensky-Marten's)*	None

produce a non-slump consistency. Add the powder to the resin portion while mixing. Mix only long enough to "wet out" the powder, but not more than one minute. Do not mix more material than can be applied in 5 to 10 minutes. Mixing ratio is 1 quart Part A to 12 pounds powder.

APPLICATION & PLACEMENT

Spread with a trowel on a properly prepared surface.

SET TIME

20 to 30 minutes (initial). The curing time of TRAFFIC-FAST™ depends upon many factors, although under most conditions traffic may be reopened in approximately 2 hours when feather-edged, and 3 to 4 hours when used to repair potholes.

CLEAN UP

Clean tools with water before TRAFFIC-FAST™ sets.

LIMITATIONS

The user is responsible for proper application. Minimum ambient and surface temperatures at 45°F and rising at time of application.

Keep container tightly closed. Not for internal consumption--consult MSDS for additional information. This product is for professional use only.

KEEP OUT OF REACH OF CHILDREN

PRODUCT ITEM # 157602
Garon and TRAFFIC FAST are trademarks of Garon Products Inc.
Made in USA.

GARON PRODUCTS INC.
P.O. Box 1924
Wall, NJ 07719-1924
800-631-5380
FAX 732-223-2002
www.garonproducts.com

Garon products are sold with the understanding that the buyer will test them in actual use and determine for himself their adaptability to his intended use. However, since such use is beyond our control, we do not guarantee the results to be obtained in the customer's processes. The information contained in this brief is advisory only, and the use of the materials and methods is solely at the risk of the user. These recommendations and suggestions for the use of our materials are in accordance with Garon standards. There are no other warranties by Garon of any nature whatsoever, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product, and under no circumstances, either expressed or implied, will GARON PRODUCTS, INC. be liable for damages in excess of the purchase price of this product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by the officers of manufacturer and seller.